



MGRZ-888

For Lead Free High Layer Count (10) Tg 180°C

Item	Test method		Test condition	Unit	Laminate	
	IPC-TM-650				IPC Spec.	Typical Value
Glass transition temp.	2.4.25		DSC	°C	Min. 170	180
CTE, X-, Y-axis	2.4.24		Pre-Tg, TMA	ppm/°C	—	12/15
			Alpha 1, TMA	ppm/°C	Max. 60	40
CTE, Z-axis	2.4.24		Alpha 2, TMA	ppm/°C	Max. 300	217
			Z-axis expansion	2.4.24	50~260°C, TMA	%
Decomposition temp.	2.4.24.26		TGA	°C	Min. 340	356
Thermal resistance (Copper removed)	2.4.24.1		T260	minutes	Min. 30	> 60
			T288	minutes	Min. 15	48
Water absorption	2.6.2.1		E-1/105+D-24/23	%	Max. 0.5	0.12
Peel strength	1 OZ	2.4.8	As received	lb/in	Min. 6	9
			After thermal stress	lb/in	Min. 6	9
Permittivity (RC 50%)	1 MHz	2.5.5.9	C-24/23/50	—	Max. 5.4	4.6
	1 GHz			—		4.4
Loss tangent (RC 50%)	1 MHz	2.5.5.9	C-24/23/50	—	Max. 0.035	0.012
	1 GHz			—		0.013
Flame resistance	UL-94		A&E-24/125	—	Min. V-0	V-0